

02.09.2014

Additive AB new

Additive for static rinses against brown discolouration

Additive AB new prevents the discolouration of EN layers after plating. The EN layers remain metallic blank, even if the goods stay in the static rinse up to 30 min. and at temperatures up to 30 °C.

Make up of the static rinse

Circulation or town water (fresh)	98 Vol.-%
Additive AB new	2 Vol.-%
Temperature	max. 30 °C
pH-value	4 – 6

The static rinse tank is filled with water to approx. 90 % of the intended end volume. While stirring add the required amount of **Additive AB new** and top up to the end volume. The pH value should now be between 4 to 5.

Bath maintenance

If the pH value is lower than 3 or higher than 7 a discolouration may happen, depending on time temperature. Should the pH value be out of the given range, caused by special production conditions, add diluted hydrochloric acid or caustic soda to adjust it.

Important note

Because of the special formulation of **Additive AB new** it is absolutely necessary, that no rinse water will be dragged out in a **DNC – electrolyte**. Such dragout will lead to a clearly slower plating speed, which is not reversible.

Waste water treatment

Static rinsing water contains nickel. It must be decontaminated and neutralised before disposal in the drain outlet to the sewer system.

Possible hazards and safety precautions

These details can be found in the material safety data sheets.

All **DNC – process** chemicals should be stored between 10 and 25 °C.

If excessive cooling should cause partial crystallisation of the solution, warm it up to > 20 °C (stirring is recommended).

Liability

This instruction manual was compiled with reference to the state of the art and all current standards, and is based on the long-term knowledge and experience of RIAG. However, RIAG cannot monitor compliance with this instruction manual and the methods described herein at the customer/end-user's premises. Work carried out with RIAG products must be adapted accordingly to meet local conditions. In particular, RIAG cannot accept liability for damage, loss or cost incurred due to a failure to adhere to this instruction manual, improper application of the methods, unauthorised technical modifications, insufficient maintenance or the absence of maintenance in respect of the requisite technical hardware or equipment, or in the event of use by unqualified personnel. RIAG is not liable for damage or loss caused by RIAG or its employees except where intention or gross negligence can be proved. RIAG furthermore reserves the right to make changes in relation to products, methods and the instruction manual without prior notice.

Our goods and services are subject to the General Terms and Conditions for Delivery of the Association of Surface Technology Suppliers (VLO), which can be viewed at www.riag.ch (link "General Terms and Conditions", document "RIAG Oberflächentechnik AG (Wängi, Switzerland) 50 KB", version 1/2014), which we would be glad to send to you on request.

This transaction is governed by material Swiss law (Law of Obligations), excluding private international law (conflict of laws) and intergovernmental treaties, specifically the CISG.

RIAG Oberflächentechnik AG
Murgstrasse 19a
CH- 9545 Wängi
Tel. + 41 (0) 52 / 369 70 70
Fax + 41 (0) 52 / 369 70 79
www.riag.ch
info@riag.ch