

25.07.2014

riag Pass 417

Trivalent temper resistant blue chromate passivation

The **riag Pass 417** is a new trivalent blue chromate process that produces glossy blue colour finish on zinc plated surfaces. The coating has high stability while tempered at 200 °C in terms of loss of colour and brightness. The coating so obtained provides corrosion resistance **without the presence of hexavalent Chrome**.

The **riag Pass 417** is supplied in easy to use liquid concentrates.

Make up

	Range	Optimum
riag Pass 417 Additive (density = 1.14 g/mL)	20 – 30 mL/L	20 mL/L
pH	1.8 – 2.2	1.9 – 2.0
Temperature	20 – 30 °C	20 – 30 °C

The higher the concentration and temperature of the solution, the lower will be the immersion time.

Procedure for a make up of 100 litres

Take 50 L DI water in the process tank. Add 2 L **riag Pass 417 Additive** and adjust the volume to 100 litres. Mix well. Adjust the pH with diluted nitric acid (or increase with a sodium carbonate anhydrous 75 g/L) and temperature of the operating bath to specified values. Now the bath is ready for operation.

Operating conditions

Temperature:	20 – 30 °C
Time:	20 – 50 sec.
pH-Value:	1.8 – 2.2 (optimum 1.9 – 2.0). Frequent control is recommended.
Agitation:	Air or parts movement
Fume extraction:	Recommended
Equipment:	Mild steel tank with polypropylene lining
Heating:	Not required or Teflon tube heaters
Pre dip activation:	This will improve the riag Pass 417 bath life as well as the adhesion and corrosion resistance. The tank make up is 0.3 – 1.0 % nitric acid. Frequent tank changes are necessary for uniform production quality.

Effluent control

The **riag Pass 417** chromate conversion coating solution is acidic and contains trivalent chromium salts. Spent solution has to be treated and discharged according to local waste water laws.

Safety considerations

Protective gear such as face shields and gloves should be worn during bath make up and operation. Chemicals shall not be stored below 10 °C.

Liability

This instruction manual was compiled with reference to the state of the art and all current standards, and is based on the long-term knowledge and experience of riag. However, riag cannot monitor compliance with this instruction manual and the methods described herein at the customer/end-user's premises. Work carried out with riag products must be adapted accordingly to meet local conditions. In particular, riag cannot accept liability for damage, loss or cost incurred due to a failure to adhere to this instruction manual, improper application of the methods, unauthorised technical modifications, insufficient maintenance or the absence of maintenance in respect of the requisite technical hardware or equipment, or in the event of use by unqualified personnel. riag is not liable for damage or loss caused by riag or its employees except where intention or gross negligence can be proved. riag furthermore reserves the right to make changes in relation to products, methods and the instruction manual without prior notice.

Our goods and services are subject to the General Terms and Conditions for Delivery of the Association of Surface Technology Suppliers (VLO), which can be viewed at www.riag.ch (link "terms and conditions" , document "General Terms and Conditions for Delivery", version 3/2018), which we gladly send you on request.

This transaction is governed by material Swiss law (Law of Obligations), excluding private international law (conflict of laws) and intergovernmental treaties, specifically the CISG.

riag Oberflächentechnik AG
Murgstrasse 19a
CH-9545 Wängi
T +41 (0)52 369 70 70
F +41 (0)52 369 70 79
riag.ch
info@riag.ch

Analysis

Sample preparation

Take the sample at a homogeneously mixed position and let it cool down to room temperature. If turbid, allow to settle and decant or filter.

Chromium (III)

Reagents	10 % Sodium hydroxide 30 % Hydrogen peroxide (H ₂ O ₂) Hydrochloric acid conc. Potassium iodide 0.1 mol/L sodium thiosulphate 1 % starch solution (freshly prepared) deionized water	
Process	10 mL 250 mL 50 mL 1 mL 0.5 mL 100 mL 20 mL 2 g 0.5 mL	Pipette passivation bath into a Erlenmeyer flask. Add deionized water and sodium hydroxide 10 % (colour change) and Hydrogen peroxide and boil the solution for 30 – 40 min. It is very important to evaporate excessive H ₂ O ₂ . Don't boil to dryness Add deionized water up to and acidify with conc. hydrochloric acid. Cool down to room temperature Add potassium iodide, titrate with 0.1 mol/L sodium thiosulphate until the solution is only slightly yellowish, then add starch solution and titrate on until the blue colour disappears.
Calculation	mL/L riag Pass 417 Additive = Consumption in mL x 7.1	

pH-Chart for riag Pass 417

value	desired						
actual	1.7	1.8	1.9	2.0	2.1	2.2	
1.0	58 mL	61 mL	63 mL	66 mL	67 mL	69 mL	Sodium carbonate (anhydrous) 75 g/L
1.1	43 mL	46 mL	48 mL	51 mL	52 mL	54 mL	
1.2	30 mL	33 mL	35 mL	37 mL	39 mL	40 mL	
1.3	23 mL	25 mL	28 mL	30 mL	32 mL	33 mL	
1.4	15 mL	18 mL	20 mL	23 mL	24 mL	25 mL	
1.5	8.5 mL	11 mL	14 mL	16 mL	18 mL	19 mL	
1.6	4.2 mL	7.1 mL	9.5 mL	12 mL	13 mL	15 mL	
1.7		2.8 mL	5.3 mL	7.8 mL	9.2 mL	11 mL	
1.8			2.47 mL	4.9 mL	6.4 mL	7.8 mL	
1.9		0.33 mL		2.47 mL	3.89 mL	5.3 mL	
2.0		0.60 mL	0.27 mL		1.41 mL	2.83 mL	Nitric acid 60%
2.1		0.78 mL	0.45 mL	0.18 mL		1.41 mL	
2.2		0.94 mL	0.61 mL	0.34 mL	0.16 mL		
2.3		1.06 mL	0.73 mL	0.46 mL	0.28 mL	0.12 mL	
2.4		1.15 mL	0.82 mL	0.55 mL	0.37 mL	0.21 mL	
2.5		1.23 mL	0.90 mL	0.63 mL	0.45 mL	0.29 mL	
2.6		1.29 mL	0.95 mL	0.69 mL	0.51 mL	0.34 mL	
2.7		1.34 mL	1.00 mL	0.74 mL	0.56 mL	0.39 mL	
2.8		1.38 mL	1.05 mL	0.78 mL	0.60 mL	0.44 mL	
2.9		1.42 mL	1.08 mL	0.82 mL	0.64 mL	0.47 mL	
3.0		1.44 mL	1.11 mL	0.84 mL	0.66 mL	0.50 mL	
3.1		1.47 mL	1.14 mL	0.87 mL	0.69 mL	0.53 mL	
3.2		1.49 mL	1.16 mL	0.89 mL	0.71 mL	0.55 mL	
3.3		1.51 mL	1.18 mL	0.91 mL	0.73 mL	0.57 mL	
3.4		1.53 mL	1.20 mL	0.93 mL	0.75 mL	0.59 mL	
3.5		1.55 mL	1.21 mL	0.95 mL	0.77 mL	0.61 mL	
3.6		1.56 mL	1.23 mL	0.96 mL	0.78 mL	0.62 mL	
3.7		1.57 mL	1.24 mL	0.97 mL	0.79 mL	0.63 mL	
3.8		1.58 mL	1.25 mL	0.98 mL	0.80 mL	0.64 mL	
3.9		1.59 mL	1.26 mL	0.99 mL	0.81 mL	0.65 mL	
4.0		1.60 mL	1.26 mL	1.00 mL	0.82 mL	0.65 mL	

In the chart above you can see the values of sodium carbonate solution or nitric acid in mL/L passivation to get the desired pH value. These values are just auxiliary and are not a guarantee. High contents of zinc and different make up concentrations will influence the values above. We recommend to adjust the pH slowly to the desired value with a recently calibrated pH meter.