

RIAG Pass 445

Trivalent thick layer passivation with high corrosion resistance

The **RIAG Pass 445** is a new trivalent chromate process that produces a greenish finish on zinc plated surfaces. The coating has a high stability while tempered at 200 °C/ 1 hour in terms of loss of brightness or colour. The coating obtained provides corrosion resistance **without the presence of hexavalent chrome**. The layer can be dyed in different colours if necessary.

The **RIAG Pass 445** is supplied as an easy to use liquid concentrate.

Make up

	Barrel	Rack
RIAG Pass 445 Additive (density = 1.14 g/mL)	12 – 15 Vol %	14 – 16 Vol %
pH	1.8 – 2.2	1.8 – 2.2
Temperature	20 – 50 °C	20 – 50 °C
Time	30 – 60 s	30 – 60 s

The higher the concentration and temperature of the solution, the lower will be the immersion time.

Procedure for a make up of 100 litres

Take 50 L DI water in the process tank. Add the **RIAG Pass 445 Additive** and adjust the volume to 100 litres. Mix well. Adjust the pH with diluted nitric acid (or increase with a 10 % solution of sodium bicarbonate) and temperature of the operating bath to specified values. Now the bath is ready for operation.

Safety considerations

Protective gear such as face shields and gloves should be worn during bath make up and operation. Chemicals shall not be stored below 10 °C.

Operating conditions

Temperature:	20 – 50 °C (optimum 40 °C)
Time:	30 – 60 s
pH-Value:	1.8 – 2.2 Frequent control is recommended.
Agitation:	Air or parts movement Do not use lead as weight for air blowing tubes!
Fume extraction:	Recommended
Equipment:	Mild steel tank with polypropylene lining
Heating:	Not required or Teflon tube heaters
Pre dip activation:	This will improve the RIAG Pass 445 bath life as well as the adhesion and corrosion resistance. The tank make up is 0.3 – 1.0 % nitric acid. Frequent tank changes are necessary for uniform production quality.
Hints:	The content of Iron must not exceed 500 mg/L, the content of Zinc 15 g/L.

Effluent control

The **RIAG Pass 445** chromate conversion coating solution is acidic and contains trivalent chromium salts. Spent solution has to be treated and discharged according to local waste water laws.

Liability

This instruction manual was compiled with reference to the state of the art and all current standards, and is based on the long-term knowledge and experience of RIAG. However, RIAG cannot monitor compliance with this instruction manual and the methods described herein at the customer/end-user's premises. Work carried out with RIAG products must be adapted accordingly to meet local conditions. In particular, RIAG cannot accept liability for damage, loss or cost incurred due to a failure to adhere to this instruction manual, improper application of the methods, unauthorised technical modifications, insufficient maintenance or the absence of maintenance in respect of the requisite technical hardware or equipment, or in the event of use by unqualified personnel. RIAG is not liable for damage or loss caused by RIAG or its employees except where intention or gross negligence can be proved. RIAG furthermore reserves the right to make changes in relation to products, methods and the instruction manual without prior notice.

Our goods and services are subject to the General Terms and Conditions for Delivery of the Association of Surface Technology Suppliers (VLO), which can be viewed at www.riag.ch (link "General Terms and Conditions", document "RIAG Oberflächentechnik AG (Wängi, Switzerland) 50 KB", version 1/2014), which we would be glad to send to you on request.

This transaction is governed by material Swiss law (Law of Obligations), excluding private international law (conflict of laws) and intergovernmental treaties, specifically the CISG.

RIAG Oberflächentechnik AG
Murgstrasse 19a
CH- 9545 Wängi
Tel. + 41 (0) 52 / 369 70 70
Fax + 41 (0) 52 / 369 70 79
www.riag.ch
info@riag.ch

Analysis

Sample preparation

Take the sample at a homogeneously mixed position and let it cool down to room temperature. If turbid, allow to settle and decant or filter.

Chromium (III)

Reagents	10 % Sodium hydroxide 30 % Hydrogen peroxide (H ₂ O ₂) Hydrochloric acid conc. Potassium iodide 0.1 mol/L sodium thiosulphate 1 % starch solution (freshly prepared)
Process	Pipette 10 mL passivation bath into a 250 mL Erlenmeyer flask, add 50 mL DI water and sodium hydroxide to a pH-value of about 10 (colour change), then add 0.5 mL Hydrogen peroxide and boil the solution for 30 – 40 min. It is very important to evaporate excessive H ₂ O ₂ (boil and reduce until shortly before crystallisation) Cool the solution, add DI water up to 100 mL and acidify with hydrochloric acid (colour change from yellow to orange), add 1 g potassium iodide, titrate with 0.1 mol/L sodium thiosulphate until the solution is only slightly yellowish, then add Some mL starch solution and titrate on until the blue colour disappears.
Calculation	Vol % RIAG Pass 445 Additive = Consumption in mL x 0.9