

25.07.2014

riag Clean 608

Acidic liquid degreasing process

riag Clean 608 is a slightly acidic degreasing process, which can be used in many applications.

Properties

- Slightly acidic (in use about pH 2.5)
- Suitable for iron and steel
- Suitable for immersion applications

Ingredients

- Organic acids
- Nonionic detergents
- Corrosion inhibitors

Make up of 100 Litres riag Clean 608

riag Clean 608 Additive,

liquid

Temperature

Time

1 – 4 L

40 – 80 °C

0.5 – 2 min.

Make up

The tank is filled to $\frac{2}{3}$ with water and heated to approx. 40 °C. Add the calculated amount of **riag Clean 608 Additive**. Finally add water up to the working level and mix well. Once the cleaner has reached its working temperature, it is ready for use.

Operating parameters

Agitation	Recommended (shorter treating time), as it supports the cleaning process
Tanks	Plastic or lined steel, when using ultrasonic high alloy steel
Heating	Immersion heaters, but thermostatic control is essential.
Fume extraction	Recommended
Water	Tap water may be taken for the makeup, however the use of low calcium or DI water is recommended.

Maintenance

Depending on the application **riag Clean 608** can be used in several concentrations. To stay in the desired working range the concentration of the cleaner has to be checked after each make up, either by analysis or by density.

Environmental considerations

All concentrates, rinse waters and waste solution must be treated and discharged in accordance with local effluent control regulations. Further information can be gleaned from the MSDS. Chemicals may not be stored below 10 °C:

Liability

This instruction manual was compiled with reference to the state of the art and all current standards, and is based on the long-term knowledge and experience of riag. However, riag cannot monitor compliance with this instruction manual and the methods described herein at the customer/end-user's premises. Work carried out with riag products must be adapted accordingly to meet local conditions. In particular, riag cannot accept liability for damage, loss or cost incurred due to a failure to adhere to this instruction manual, improper application of the methods, unauthorised technical modifications, insufficient maintenance or the absence of maintenance in respect of the requisite technical hardware or equipment, or in the event of use by unqualified personnel. riag is not liable for damage or loss caused by riag or its employees except where intention or gross negligence can be proved. riag furthermore reserves the right to make changes in relation to products, methods and the instruction manual without prior notice.

Our goods and services are subject to the General Terms and Conditions for Delivery of the Association of Surface Technology Suppliers (VLO), which can be viewed at www.riag.ch (link "terms and conditions", document "General Terms and Conditions for Delivery", version 3/2018), which we gladly send you on request.

This transaction is governed by material Swiss law (Law of Obligations), excluding private international law (conflict of laws) and intergovernmental treaties, specifically the CISG.

riag Oberflächentechnik AG
Murgstrasse 19a
CH-9545 Wängi
T +41 (0)52 369 70 70
F +41 (0)52 369 70 79
riag.ch
info@riag.ch

Analysis (Analytical methods)

Sample preparation:

Take sample from a well-mixed location and allow to cool down to 25 °C.

Reagents: Sodium hydroxide 0.1 mol/L
Phenolphthalein solution 0.1 % in ethanol

Procedure: 10 mL **riag Clean 608** is transferred via pipette into a
250 mL beaker, add
100 mL deion. water, add
5 drops phenolphthalein solution
Titrate with sodium hydroxide 0.1 mol/L from colourless to pink violet

Calculation: **riag Clean 608 Additive** (mL/L) = use of NaOH in mL x 2.52

Should the cleaner despite proper maintenance not work satisfactory anymore, a new make up is necessary.

Attention:

Chemicals not intended to be added to the process may disturb and influence the quality of the processed surfaces.