

RIAG Cr 330

Hard chromium electrolyte with high current efficiency

The hard chromium process **RIAG Cr 330** deposits hard chromium layers which excels in the following benefits:

Properties

- High plating speed (up to 1 µm/min)
- Bright coatings
- Fluoride free, therefore only slight attack on iron
- Hardness of approximately 1000 HV (0,1)
- Micro-cracked deposits
- High cathodic current efficiency (up to 26 %)
- Good throwing power

Make up values

	Target value	Optimum
Chromium trioxide (CrO ₃)	280 – 320 g/L	300 g/L
RIAG Cr 330 Make up	45 – 55 mL/L	50 mL/L
Sulphuric acid 96 % chemical pure (H ₂ SO ₄)	1.6 – 2.4 mL/L	2 mL/L

The necessary quantity of chromic acid has to be dissolved in 70 % of the final electrolyte volume. For the make up and the current level balance deionised water is necessary. After the dissolution of the chromic acid the necessary quantity **RIAG Cr 330 Make up** and the sulphuric acid has to be added. Now add the deionised water until the final electrolyte volume is reached and mix well.

Afterward the electrolyte has to be worked through during 2 to 3 hours.

We recommend the application of **RIAG Cr 320 Tenside** for the reduction of atomised spray.

Equipment / Working conditions

Tank material:	SM-steel with rubber or special plastic lining
Heating:	Immersion heaters (porcelain or PTFE)
Anodes:	We recommend the application of platinized titanium anodes. By using them, make sure, that the platinum surface is covered with a lead dioxide film (brown-black layer). The lead dioxide film is obtained using one or more lead alloy anodes together with the platinized titanium anodes. Only under this condition Cr^{3+} is oxidized to Cr^{6+} (important, because otherwise the value of chromium-(III) increases too much). The ratio of the anode and cathode surface should be 2.5 : 1.
Temperature:	55 – 60 °C
Voltage:	6 – 12 volt (max. 15 volt)
Current density:	50 A/dm ² (20 – 60 A/dm ²)
Anodic current density:	20 – 30 A/dm ²
Rectifiers:	12 volt units, respectively 15 volt units for higher outputs. The residual ripple must be below 5 %.
Exhaust:	An exhaust is absolutely necessary.
Deposition rate:	At 55 A/dm ² the chromium deposition rate is around 1 µm/min.

Electrolyte control and maintenance

Regular analysis of the chromic and sulphuric acid are necessary.

Electrolyte values:	Target value	Optimum
Chromium trioxide (chromic acid)	280 – 320 g/L	300 g/L
Sulphuric acid (referred to the concentration of chromic acid)	1.1 – 1.4 %	1.25 %
Chromium-(III)-oxide	2 – 6 g/L	3 g/L

Reinforcement: Per 10 kg chromic acid add 1 L **RIAG Cr 330 Replenisher**. Missing sulphuric acid has to be added with chemical pure sulphuric acid.

Barium carbonate: To reduce (precipitate) 1 g of sulphuric acid 2.2 g barium carbonate are necessary.

Mode of operation of RIAG Cr 330 Replenisher

An insufficiency of **RIAG Cr 330 Replenisher** results in milky dull deposits. Both the plating speed and the hardness of the chromium deposits will be lessened. The number of micro cracks lowers also and lessened the good layer quality.

An excess heads towards burnings in the areas with high current density. A too high concentration of **RIAG Cr 330 Replenisher** can be dropped only by diluting the electrolyte.

To guarantee a failure-free operation we recommend sending an electrolyte sample frequently to the RIAG laboratory in order to analyse it.

Supply inventory

To guarantee a failure-free production a supply inventory is essential. We recommend the following quantities per 1000 L electrolyte:

RIAG Cr 330 Replenisher	25 kg
Chromium trioxide (chromic acid)	50 kg
Sulphuric acid 96 % chemical pure	1 kg
Barium carbonate	1 kg

Safety arrangements

We recommend wearing safety glasses, gloves and protective clothing during working with chromic acid. For further information please consult the material safety data sheets.

Waste water treatment / Environmental protection

The concentrates as well as their rinsing waters contain chromium (VI) and are extremely dangerous for waste water treatment plants. The waste water needs to be prepared according legal regulations before getting in the canalisation.

Liability

This instruction manual was compiled with reference to the state of the art and all current standards, and is based on the long-term knowledge and experience of RIAG. However, RIAG cannot monitor compliance with this instruction manual and the methods described herein at the customer/end-user's premises. Work carried out with RIAG products must be adapted accordingly to meet local conditions. In particular, RIAG cannot accept liability for damage, loss or cost incurred due to a failure to adhere to this instruction manual, improper application of the methods, unauthorised technical modifications, insufficient maintenance or the absence of maintenance in respect of the requisite technical hardware or equipment, or in the event of use by unqualified personnel. RIAG is not liable for damage or loss caused by RIAG or its employees except where intention or gross negligence can be proved. RIAG furthermore reserves the right to make changes in relation to products, methods and the instruction manual without prior notice.

Our goods and services are subject to the General Terms and Conditions for Delivery of the Association of Surface Technology Suppliers (VLO), which can be viewed at www.riag.ch (link "General Terms and Conditions", document "RIAG Oberflächentechnik AG (Wängi, Switzerland) 50 KB", version 1/2014), which we would be glad to send to you on request.

This transaction is governed by material Swiss law (Law of Obligations), excluding private international law (conflict of laws) and intergovernmental treaties, specifically the CISG.

RIAG Oberflächentechnik AG
Murgstrasse 19a
CH- 9545 Wängi
Tel. + 41 (0) 52 / 369 70 70
Fax + 41 (0) 52 / 369 70 79
www.riag.ch
info@riag.ch